





Elastic adhesives and sealants

# Silicones

### Silicone HT 300



#### High-temperature-resistant | acetoxy-curing

WEICON HT 300 is red, high-temperature-resistant (+300 °C /+572 °F), free of solvents, strong, and acetoxy-curing. It is resistant to weathering, ageing and chemicals and is extremely elastic (breaking elongation of approx. 300%).

The product is particularly suitable for heat-exposed bonds and seals and adheres very well to steel, aluminium, glass, ceramics and many other materials.

The adhesive and sealant can be used in industrial furnaces, flue gas systems, heating installations, exhaust gas routing, heating cabinets and in many additional areas.

Technical Data		
Base		1-C. polysiloxane (acetate)
Colour		red
Texture		pasty
Can be painted		No
Cure type		moisture-curing
Stability/run-off	ASTM D 2202	1.0 mm
Density		1,18 g/cm³
Curing condition		from +5°C to +40°C and 30% to 95% rel. air air humidity
Processing temperature		+5°C to +35°C
Curing speed	in the first 24 h	2 -3 mm
Skin-over time		8 min.
Gap bridging up to max.		5 mm
Max. sealing joint width		25 mm
Tensile strength	ISO 37 / S3A	2,5 N/mm²
Elongation at break (tensile)	ISO 37, S3A	300 %
Elongation at 100 %	ISO 37 S3A	0,9 N/mm²
Movement absorption max.		15 %
Volume change	DIN 52451	< -6 %
Hardness (Shore A)	DIN ISO 7619	30±5
Temperature resistance		-40 °C to briefly +280 °C (approx. 2 h) +300 °C
Building material class	DIN 4102	B 2
Minimum shelf life	at room temperature	12 mon.
Approvals / Guidelines		
ISSA Code		75.634.20/21
IMPA Code		815282/83

### **Surface Pre-Treatment**

Surfaces must be clean and free of grease. Many surface soilings, such as oil, grease, dust and dirt can be removed with WEICON Surface Cleaner. For heavily soiled metal surfaces, we recommend Cleaner Spray S; for removing old colour residues or adhesive residues, WEICON Sealant and Adhesive Remover is ideal. Most materials can be bonded to and among each other. For certain materials or special requirements, we recommend the use of a bonding agent (primer). Mechanical surface pre-treatment e.g. by grinding or sanding can also improve the adhesion considerably.

### **Processing**

**Processing Cartridge** 

gun for 310 ml cartridges, compressed air gun, we recommend a version with piston rod (WEICON Compressed Air Cartridge Gun), automatic dosing systems. Squeeze out by hand, close tube again immediately after use, opened tubes should be used up as quickly as possible

Joining the components

In order to guarantee and ideal wetting, the bonding parts need to be joined, before the adhesive skins over (skin-over time).

Note
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.





Elastic adhesives and sealants

## **Silicones**

## Silicone HT 300

### **Storage**

Store in the unopened original container at room temperature. Avoid sources of heat and direct sunlight.

### Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

### **Accessories**

10025241 V-Joint Nozzle, 1 PCE

Compressed Air Cartridge Gun, 1 PCE 10033114

Cartridge Gun Special, 1 PCE 10020751

Cartridge Gun, 1 PCE 10000441

### Available sizes

10000432	Silicone HT 300, 310 ml, red
10005243	Silicone HT 300, 85 ml, red

10104027 Silicone HT 300, 280 ml (Green Tube), red

10104059 Silicone HT 300, 1 Set, red

10104250 Silicone HT 300, 280 ml (plastic bag), red



Note
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.