

# Technical Datasheet DanBond A10

## **Thixotropic Black Acrylic adhesive**

#### **Product Description**

**DanBond A10** is a two component structural methacylate adhesive, designed for the bonding of high strength metal and composite applications in the automotive industry. **A10** has been formulated from innovative technology, including our revolutionary adhesion system. This unique system enables the **A10** to achieve the ultimate balance of mechanical strength and impact resistance whilst still remaining both simple and quick to use.

### **Typical Applications**

DanBond A10 is very versatile, and can bond a wide variety of substrates without the need for surface primers or conditioners. Typical examples shown below:

- Bonding metal fasteners to moulded composite parts
- · Bonding and repairing caravan GRP body panels
- · Bonding and repairing plastic bumpers and trims.
- Bonding deck fittings and molded parts in the marine industry.

#### Instructions For Use

- 1. Always consult MSDS before using A10 for the first time.
- 2. Carry out surface preparation where required. \*
- 3. Remove cap, and attach mixer nozzle.
- 4. Dispense sufficient adhesive to ensure equal mix.
- 5. Apply adhesive to one suface and assemble components carefully, clamping if required.
- 6. It is always easier to remove any excess adhesive prior to cure using a suitable cleaner \*
- Allow the adhesive sufficient time to achieve handling strength before moving or unclamping components.

# **Properties of Uncured Material**

| Resin                      | Methyl Methacrylate   |
|----------------------------|-----------------------|
| Colour                     | Black                 |
| Appearance                 | Thixotropic Gel       |
| Viscosity Brookfield T Bar | 120,000 to 150,000cps |
| Cure System                | Exothermic            |
| Open Time                  | 12-15 Minutes @ 20°C  |
| Handling Strength          | 20-25 Minutes @ 20°C  |

#### **Performance of Cured Material**

| ASTM D1002 Lapshear        | Up to 30 Nmm²  |
|----------------------------|----------------|
| ASTM D638 Tensile Strength | Up to 30 Nmm²  |
| Gap Fill                   | 5mm            |
| Temperature Range          | -55°C to 120°C |

#### **Packaging**

DanBond A10 is available in 50ml

# Storage & Shelflife

DanBond A10 should be stored unopened in a cool dry location, out of direct sunlight. Stored correctly, this grade can offer a 12 month shelf life from manufacture.

# Health and Safety in Use

DanBond A10 is a methyl methacrylate and should not be used without consulting the MSDS, which contains full information regarding the use of this product, including Transport, Disposal, Toxicological, Exposure Controls, Accidental Release and First Aid measures essential to the safe use of this product.