

Technical Datasheet



Aluminium Spray A-100



excellent corrosion protection abrasion resistant

WEICON Aluminium Spray A-100 is abrasion-proof, resistant to many diluted acids and lyes, as well as to atmospheric influences. It contains aluminium pigments with a purity grade of <>99.5%.

WEICON Aluminium Spray A-100 offers high-grade corrosion protection for all metal surfaces.

WEICON Aluminium Spray A-100 can be used in cooling and ventilation technology, combustion systems, pipelines and machine housings, fibre glass car body components, in model building, arts and crafts, toy manufacturing and in many additional applications.

Technical Data

Colour	aluminium metallic, matt
Application range	indoors and outdoors
Binding agent	acrylic resin
Pigment	Aluminium pigments
Pigment purity	approx. 99,5% Al
Percentage of metal in dry film	43 %
Specific weight	0,9 - 1,0 g/cm³
Recommended primer	Zinc-Spray
Processing temperature	+5 to +35, optimal +18 to +35 °C
Consumption at 1.5 cross coats	120 ml/m²
Layer thickness at 1.5 cross coats	25 -35 μm
Dust dry after	10 min.
Hardened after	4 -6 h
Overpaintable after	4-6 h
Abrasion-resistant yes/no	abrasion-resistant
Cross cutting DIN 53151/ ISO 2409	cross cut characteristic value GT 0 to GT 1
Mandrel bend test DIN EN ISO 1519	no hair cracking

Top coating	not required
Storage stability	24 months
Temperature resistance	-50 to +800 °C
ISSA-Code	53.402.42
IMPA-Code	450814

^{*}Ab +350°C nicht abriebfest

Surface pre-treatment

Clean and degrease surfaces with WEICON Surface Cleaner.

Processing

Clean and degrease surfaces with Cleaner S. Shake can before use till the mixing ball can be heard. Spray on evenly and crosswise at room temperature (approx. +20°C) and at about 25 cm distance from surface. Dust-dry after approx. 10 minutes, fully hardened after approx. 4-6 hours.

Storage

Pressurized container: protect from sunlight and do not expose to temperatures exceeding +50°C.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

11050400 Aluminium Spray A-100 400 ml

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0

WEICON SA (Pty) Ltd phone +27 (0) 21 709 0088 info@weicon.co.za www.weicon.co.za

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae www.weicon.ae

WEICON South East Asia Pte Ltd Singapore phone (+65) 6710 7671 info@weicon.com.sg www.weicon.com.sg

WEICON Inc Canada phone +1 877 620 8889 info@weicon.ca www.weicon.ca

WEICON Czech Republic s.r.o. phone +42 (0) 417 533 013 www.weicon.cz

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr www.weicon.com.tr

WEICON Ibérica S.L. phone +34 (0) 914 7997 34 info@weicon.es www.weicon.es

DANLUBE A/S Tune Parkvej 5 DK-4030 Tune Denmark +45 70 25 12 80 info@danlube.dk www.danlube.dk