

# Easy-Mix N 5000 Epoxy Adhesive



**almost colourless/crystal clear liquid, self-levelling shorter pot life**

Easy-Mix N 5000 is transparent, liquid, self-levelling, has a pot life of 20 minutes and a high adhesive strength.

It can be used for many materials, such as metal, plastic, fiber composites, ceramic, glass, stone and wood. It is suited for connections where a transparent bond is important.

## Technical Data

Base	Epoxy resin unfilled
Texture	liquid
Colour	almost colourless, glass clear
Mixing ratio by weight (Resin / Hardener)	1:1
Density of the mixture	1,07 g/cm <sup>3</sup>
Viscosity of the mixture at 20°C (+68°F)	5.000 mPa·s
Adhesive gap bridging up to max.	2 mm
Processing temperature	+10 to +35 °C
Curing temperature	+6 to +40 °C
Pot life at 20°C (+68°F) for 10ml material	20 min.
Handling strength (35% strength) after	60 min.
Capable of bearing mechanical loads (50% strength) after	3 h
Final strength (100%) after	48 h
Medium strength of the pure epoxy resin according to DIN EN 1465	
Pressure	10 Mpa
Pull	40 Mpa
Bending	50 Mpa
Tg after curing at room temperature	52,4 °C
Tg after tempering (at 120 °C)	54,2 °C
E-Modul	1.700 - 2.000 Mpa
Shore hardness D	65
Medium shear strength according to DIN EN 1465 at	

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Steel sand blasted	21 N/mm <sup>2</sup>
Alu sandblasted	19 N/mm <sup>2</sup>
PVC hard-roughened	14 N/mm <sup>2</sup>
Linear shrinkage	2,0 %
Temperature resistance	-50 to 100 °C
Thermal diffusivity (23 °C)	0,121 mm <sup>2</sup> /s
Thermal conductivity	0,14 W/m·K
Specific heat capacity	1,531 J/(g·K)
Resistivity	1,59 · 10 <sup>12</sup> Ωm

### Surface pre-treatment

To ensure a perfect bond, the surfaces to be joined must be clean and dry (e.g., clean and degrease using WEICON Surface Cleaner).

### Processing

WEICON Easy-Mix products can be processed directly from the double cartridges with the help of the included static mixer. Reject the first 5 cm of the dosed bead. Apply adhesive to only one of the surfaces to be bonded. The pot life given is for a material quantity of 10 ml at room temperature. If larger quantities are used, the curing time will be faster. Similarly, higher ambient temperatures shorten the cure times (as a rule of thumb, every +10°C increase above room temperature will halve working and curing time). Temperatures below +16°C will extend working and curing times considerably, while below about +5°C, no reaction will take place at all.

### Storage

When kept at a constant room temperature of about +20°C and unopened in dry conditions, WEICON Epoxy Adhesives will keep for at least 18 months. Avoid direct sunlight. If these storage instructions are disregarded, the storage life will be reduced to 6 months. Epoxy resins are fundamentally liable to crystallise at temperatures of less than +5°C. This effect is accentuated by wide variations in temperature such as can frequently occur during transport in winter. This also has a negative effect on working qualities, curing and technical details, although these effects can be reversed by warming up to a maximum of +50°C (no naked flame). In the case of WEICON Epoxy Adhesives, careful selection and combination of the base resins (bisphenol A and F) ensures a reduction of crystallisation.

### Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Available sizes:

10650250 Easy-Mix N 5000 Epoxy Adhesive 50 ml

### Accessories:

10650005 Mixing Nozzles Easy-Mix

10653050 Dispenser D 50, 50 ml

12955175 Dosing Tips,

WEICON GmbH & Co. KG  
(Headquarters)  
Germany  
phone +49 (0) 251 9322 0  
info@weicon.de  
www.weicon.de

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae  
www.weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca  
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Turkey  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr  
www.weicon.com.tr

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za  
www.weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
phone (+65) 6710 7671  
info@weicon.com.sg  
www.weicon.com.sg

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz  
www.weicon.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es  
www.weicon.es

**DANLUBE A/S**  
Tune Parkvej 5  
DK-4030 Tune  
Denmark  
+45 70 25 12 80  
[info@danlube.dk](mailto:info@danlube.dk)  
[www.danlube.dk](http://www.danlube.dk)