

## Easy-Mix RK-7200 Structural Acrylic Adhesive



**transparent**  
**high strength**  
**impact resistant, residual elasticity**

WEICON Easy-Mix RK-7200 is a high strength, solvent-free and fast-curing structural adhesive. It is based on MMA (methyl methacrylate) and has an excellent adhesion on many materials.

Because of the transparent curing, RK-7200 is particularly suitable for transparent joints where the bonding seams should not be visible. This adhesive can also be used for structural bondings where a coloured adhesive would not fit optically to the construction parts.

Thus, transparent plastics like e. g. acrylic glasses (PMMA) and other materials can be bonded in a clean and appealing way.

### Technical Data

Base	Methyl methacrylate
Mixing ratio resin/hardener	1:1
Colour after curing	transparent, colourless
Density of the mixture	1,2 g/cm <sup>3</sup>
Viscosity of the mixture	5.000 - 8.000 mPa·s
Application procedure	Easy-Mix
Texture	viscous
Pot life at +20°C (+68°F)	1 - 2 min.
Handling strength (35% strength) after	8 min.
Capable of bearing mechanical loads (50% strength) after	120 min.
Processing temperature	+10 to +40 °C
Curing temperature	+18 °C
Final strength (100%) after	6 h
Adhesive gap bridging	0,1 - 2,0 mm
Shear strength according to DIN EN 1465 at:	
Aluminium	8 N/mm <sup>2</sup>
Steel sand blasted	18 N/mm <sup>2</sup>

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Stainless Steel	18 N/mm <sup>2</sup>
PC	7 N/mm <sup>2</sup>
Tg after curing at room temperature	-17,5 °C
PMMA	9 N/mm <sup>2</sup>
ABS	7 N/mm <sup>2</sup>
Hard-PVC	8 N/mm <sup>2</sup>
GRP	9 N/mm <sup>2</sup>
CFK	12 N/mm <sup>2</sup>
Polyamide 6.6	2 N/mm <sup>2</sup>
Temperature resistance	-40 to +120 °C

### Surface pre-treatment

The prerequisite for perfect adhesion are clean and dry surfaces (e.g. cleaning and degreasing with WEICON Surface Cleaner). The highest strength values can be achieved through additional pre-treatment of the surfaces, such as roughening using blasting or abrasive agents. Several plastics, in particular polyamide, Teflon®, polyolefin etc. can only be bonded after special surface treatment, for example using fluoridation, low-pressure plasma, corona, flame impingement etc.

### Processing

WEICON Easy-Mix products can be processed directly from the double cartridges with the help of the included static mixer. Reject the first 5 cm of the dosed bead. Apply adhesive to only one of the surfaces to be bonded. The pot life given is for a material quantity of 10 ml at room temperature. If larger quantities are used, the curing time will be faster. Similarly, higher ambient temperatures shorten the cure times (as a rule of thumb, every +10°C increase above room temperature will halve working and curing time). Temperatures below +16°C will extend working and curing times considerably, while below about +5°C, no reaction will take place at all.

### Storage

6 months at 0°C to +4°C 3 months at 20°C to 25°C

### Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Available sizes:

10564050 Easy-Mix RK-7200 Structural Acrylic Adhesive 50 g

### Accessories:

10650005 Mixing Nozzles Easy-Mix,  
10653050 Dispenser D 50, 50 ml  
12955175 Dosing Tips,

WEICON GmbH & Co. KG  
(Headquarters)  
Germany  
phone +49 (0) 251 9322 0  
info@weicon.de  
www.weicon.de

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae  
www.weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca  
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Turkey  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr  
www.weicon.com.tr

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za  
www.weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
phone (+65) 6710 7671  
info@weicon.com.sg  
www.weicon.com.sg

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz  
www.weicon.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es  
www.weicon.es

**DANLUBE A/S**  
Tune Parkvej 5  
DK-4030 Tune  
Denmark  
+45 70 25 12 80  
info@danlube.dk  
www.danlube.dk