

Technical Datasheet

Create Date: 17 08 2020 - Seite 1/2



Flex 310 M® Stainless Steel



Shore A hardness (DIN 5355 / ASTM D 224) ± 5 Elongation at break (DIN 53504/ASTM D 2240) ± 5 Tensile strength of pure adhesive and sealant Average tensile shear strength (DIN EN 1465/ASTM D 12) Tear strength (DIN 53515/ASTM D 1002) Movement capacity max.	
Tensile strength of pure adhesive and sealant Average tensile shear strength (DIN EN 1465/ ASTM D 12) Tear strength (DIN 53515/ASTM D 1002)	45
Average tensile shear strength (DIN EN 1465/ ASTM D 12) Tear strength (DIN 53515/ASTM D 1002)	280 %
Tear strength (DIN 53515/ASTM D 1002)	3,1 N/mm²
	2,5 N/mm²
Movement capacity max.	11 N/mm²
	20 %
Building material category (DIN 412)	B 2
Temperature resistance -40 to +5	90 (briefly up to +120) ℃
ISSA-Code	75.634.33
IMPA-Code	81 52 74

^{*}Measured at 50% relative air humidity and +23°C

suitable for universal use

WEICON Flex 310 M Stainless-Steel adhesive and sealant is noncorrosive, strong, overpaintable (wet in wet), sandable, resistant to aging and UV rays and is free of silicone, isocyanate, halogens or solvents

WEICON Flex 310 M Stainless-Steel has an ISEGA certificate and can be used as an adhesive in food technology.

Flex 310 M Stainless-Steel can also be used in all application fields where the colour of the adhesive and sealant must match the surface material (e. g. stainless steel, aluminium, etc.).

WEICON Flex 310 M Stainless-Steel can be used in metal construction, tank and apparatus engineering, food industry, in kitchen and sanitary installations, ventilation and air conditioning systems, and in all applications where silicones or products containing silicones are not suitable.





Technical Data

Base	1 CMS Polymer
density	1,08 g/cm³
Viscosity adhesive	pasty
Stability/Run-off (ASTM D 222)	< 1 mm
Processing temperature	+5 to +30 °C
Cure type	By humidity
Curing condition	+5 to +40°C and 30% to 95% rel. humidity
Skin-overtime*	15 min.
Curing speed (first 24h)	3 mm
Volume change (DIN 52451)	-1 %
Gap filling up to max.	5 mm
Gap width up to max.	25 mm

Surface pre-treatment

The surfaces must be clean and free of grease. Many surface contaminants, e.g. oil, dust and dirt, can be removed with WEICON Surface Cleaner. For heavily soiled metal surfaces, we recommend WEICON Cleaner Spray S; WEICON Sealant and Adhesive Remover is suitable for removing old paint or adhesive residues. Most materials can be bonded well to themselves and among each other. For certain materials or extreme requirements, we recommend the use of an adhesion agent (primer). Detailed information on this subject is contained in the primer selection table. A mechanical surface pre-treatment, e.g. sanding or sand-blasting, can considerably improve the adhesion.

Processing

Application methods

Professional cartridge gun for 310 ml cartridges, compressed air gun (we recommend a variation with piston rod), automatic dosing systems.

Joining the parts to be bonded

To ensure optimal wetting, the parts must be joined before the first skin has been formed on the adhesive (skin-overtime).

Storage

When unopened and stored at room temperature (+23°C and 50 % rel. humidity), WEICON elastic one-component adhesives and sealants have a shelf life of 12 months.

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de www.weicon.de

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za www.weicon.co.za WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae www.weicon.ae

WEICON South East Asia Pte Ltd Singapore phone (+65) 6710 7671 info@weicon.com.sg www.weicon.com.sg WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz www.weicon.cz WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr www.weicon.com.tr

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es www.weicon.es **DANLUBE A/S**Tune Parkvej 5

DK-4030 Tune
Denmark
+45 70 25 12 80
info@danlube.dk
www.danlube.dk



Technical Datasheet

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

13656310 Flex 310 M® Stainless Steel 310 ml

Accessories:

13250000 Cartridge Cutter, 310 ml 13250001

Cartridge Gun, 13250002 Cartridge Gun Special,

Compressed Air Cartridge Gun, 13250009

13955031 V-Joint Nozzle,

Note
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.