

# Repair Stick Multi-Purpose



**Fast-curing, mineral-filled  
drinking water approval**

**Temperature resistance: -25°C (-13°F) to +120°C (+248°F)**

The all-round product for quick, permanent, elastic and nonshrinking repairs and touch-ups on nearly all surfaces. Repair Stick Multi fills and seals cracks, holes, damages and leaks. It can be used on metal, wood, stone, glass, plastic and many other materials. Thanks to its versatile use, WEICON Repair Stick Multi can be used in various industrial fields as well as in trades and the DIY sector.



## Technical Data

Base	epoxy resin mineral-filled
Texture	pasty
Mixture (weight %) resin/hardener	1:1
Colour after curing	white
Density of the mixture	1,9 g/cm³
Gap bridging max.	15 mm
Processing temperature	+10 to +40 °C
Curing temperature	+6 to +40 °C
Pot life for 25gr preparation and +20°C (+68°F)	4 min.
Handling strength (35% strength) after	15 min.
Capable of bearing mechanical loads (50% strength) after	60 min.
Final strength (100%) after	24 h
Pressure (DIN 53281-83)	40 N/mm²
Medium shear strength after 7 days at +20°C (+65°F) DIN EN 1465 at	Steel, sandblasted: 6,5 N/mm²
Shore hardness D	70
Thermal conductivity (ASTM D 257)	0,40 W/m·K

## Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Linear shrinkage	0,02 %
Dielectric strength (ASTM D 149)	3,0 kV/mm
Thermal expansion coefficient (ISO 11359)	30-40 x 10 <sup>-6</sup> K <sup>-1</sup>
Temperature resistance	-25 to +120, short-term up to +150 °C

## Surface pre-treatment

To ensure a perfect bond, the surfaces to be joined must be clean and dry (e.g., clean and degrease using WEICON Surface Cleaner).

## Processing

WEICON Repair Sticks cover gaps of max. 15 mm per procedure. The pot life given is for a material quantity of 25 g at room temperature. If larger quantities are used, the curing time will be faster due to the typical reaction heat of epoxy resins (exothermic reaction). Similarly, higher ambient temperatures shorten the cure time (as a rule of thumb, every +10°C increase above room temperature will halve working and curing time). Temperatures below +16°C will extend working and curing times considerably, while below about +5°C, no reaction will take place at all.

## Storage

When kept at a constant room temperature of about +20°C and unopened in dry conditions, WEICON Repair Sticks will keep for at least 18 months. Avoid direct sunlight.

## Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Available sizes:

1053905 /	Repair Stick Multi-Purpose 5 / g
10539115	Repair Stick Multi-Purpose 115 g

WEICON GmbH & Co. KG  
(Headquarters)  
Germany  
phone +49 (0) 251 9322 0  
info@weicon.de  
[www.weicon.de](http://www.weicon.de)

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za  
[www.weicon.co.za](http://www.weicon.co.za)

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae  
[www.weicon.ae](http://www.weicon.ae)

WEICON South East Asia Pte Ltd  
Singapore  
phone +65 (65) 6710 7671  
info@weicon.com.sg  
[www.weicon.com.sg](http://www.weicon.com.sg)

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca  
[www.weicon.ca](http://www.weicon.ca)

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz  
[www.weicon.cz](http://www.weicon.cz)

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Turkey  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr  
[www.weicon.com.tr](http://www.weicon.com.tr)

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es  
[www.weicon.es](http://www.weicon.es)

**DANLUBE A/S**  
Tune Parkvej 5  
DK-4030 Tune  
Denmark  
+45 70 25 12 80  
[info@danlube.dk](mailto:info@danlube.dk)  
[www.danlube.dk](http://www.danlube.dk)