

## Adhesive Spray



### Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Available sizes:

11800500 Adhesive Spray 500 ml

### universal use

WEICON Adhesive Spray can be used universally and bonds light materials to themselves and among each other.

Adhesive Spray is suitable for the bonding of numerous materials such as paper, cardboard, pasteboard, wood, thin veneers, cork, leather, textiles, felt, soft foam, rubber, foam rubber, and plastic film (except for PVC and polyethylene). It is especially suited for the bonding of hard foam (e.g. polystyrene).

### Technical Data

Base	synthetic rubber
Processing temperature	+10 to +30 °C
Evaporation time	5 - 15 min.
Open time max.	30 min.
Effectiveness	4 m <sup>2</sup>
Temperature resistance	-20 to +65 °C
Storage stability	12 months

### Processing

1. Shake can before use. Surfaces must be dry, clean and free of grease. Spray on one surface at about 15 to 30 cm distance. With porous materials, Adhesive Spray should be applied on both surfaces.
2. Depending on surface characteristics and ambient temperature, let the spray dry for 1 - 15 minutes until the adhesive is no longer stringy.
3. Position the parts and join them with strong pressure.
4. The spray head can be set to horizontal or vertical spray jet

### Storage

Pressurized container: protect from sunlight and do not expose to temperatures exceeding +50°C.

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG  
(Headquarters)  
Germany  
phone +49 (0) 251 9322 0  
info@weicon.de  
www.weicon.de

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae  
www.weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca  
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Turkey  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr  
www.weicon.com.tr

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za  
www.weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
phone (+65) 6710 7671  
info@weicon.com.sg  
www.weicon.com.sg

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz  
www.weicon.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es  
www.weicon.es

**DANLUBE A/S**  
Tune Parkvej 5  
DK-4030 Tune  
Denmark  
+45 70 25 12 80  
[info@danlube.dk](mailto:info@danlube.dk)  
[www.danlube.dk](http://www.danlube.dk)