

WEICON Ceramic BL



**flowable | mineral-filled | extremely wear-resistant |
temperature-resistant up to +180°C (+356°F)**

WEICON Ceramic BL is filled with silicon carbide and zirconium silicate, resistant to chemicals and offers extreme wear protection and high abrasion resistance. The epoxy resin system is particularly suited for the lining of heavily stressed pump housings, as wear protection for slide bearings, slides, funnels and pipes and for the repair of castings, valves and blower fans. The product can be used in mechanical and plant engineering, in equipment engineering, and in many other areas of industry. Wear-resistant final coating for all Plastic Metal types. WEICON Ceramic BL is also well-suited for creating a system structure in combination with WEICON GL. Due to the different colours of the two wear protection systems, the degree of wear can be easily determined during visual inspections.

Characteristics

| | |
|---------|--|
| Base | epoxy |
| Filler | silicon carbide, zirconium silicate |
| Texture | flowable |
| Colour | blue |

Processing

| | | |
|--------------------------|------------------------|--------------|
| Processing temperature | +15°C to +40°C | |
| Component temperature | >3 °C above dew point | |
| relative air humidity | < 85 % | |
| Mixing ratio by weight | 100:8 | |
| Mixing ratio by volume | 100:15 | |
| Viscosity of the mixture | at +25 °C | 23.000 mPa·s |
| Density of the mixture | 1,8 g/cm³ | |
| Consumption | Layer thickness 1.0 mm | 1.8 kg/m² |
| max. layer thickness | per step | 10 mm |

Curing

| | | |
|------------------------|-----------------------|---------|
| Pot life | at 20 °C, 500 g batch | 55 min. |
| Additional layer after | (35 % strength) | 5 h |
| Working strength after | (80 % strength) | 8 h |
| Final strength | (100 % strength) | 12 h |
| Shrinkage | 0,13 % | |

Mechanical properties after curing

| | | |
|---|---------------------|---------------|
| - measured after curing at | 24 h RT + 4 h 60 °C | |
| Tensile strength | DIN EN ISO 527-2 | 59 MPa |
| Elongation at break (tensile) | DIN EN ISO 527-2 | 0.9 % |
| E-modulus (tensile) | DIN EN ISO 527-2 | 7100-7300 MPa |
| Compressive strength | DIN EN ISO 604 | 116 MPa |
| Bending strength | DIN EN ISO 178 | 80 MPa |
| Hardness (Shore D) | DIN ISO 7619 | 90±3 |
| Adhesive strength | DIN EN ISO 4624 | 17 MPa |
| Lap shear strength material thicken. 1,5mm DIN EN 14625 | | |
| Steel 1.0338 sandblasted | 12 MPa | |
| Stainless steel V2A sandblasted | 11 MPa | |
| Aluminium sandblasted | 7 MPa | |
| Galvanized steel | 4 MPa | |

Thermal parameters

| | | |
|-------------------------------------|--------------------|--------------|
| Temperature resistance | -35°C to +180°C | |
| Tg after curing at room temperature | (DSC) | ~ +52 °C |
| Tg after tempering (at 120°C) | (DSC) | +69 °C |
| Heat deflection resistance | DIN EN ISO 75-2 | +55 °C |
| Thermal conductivity | DIN EN ISO 22007-4 | 0,6 W/m·K |
| Heat capacity | DIN EN ISO 22007-4 | 0,91 J/(g·K) |

Electrical parameters

| | | |
|------------|------------------|--------------------------|
| Resistance | DIN EN 62631-3-1 | 5,8·10 ¹¹ Ω·m |
| magnetic | no | |

Specific properties

| | | |
|-----------------------|--------------------------------|--|
| IMPA Code | 812937/38 | |
| ISSA Code | 75.509.19/20 | |
| Marinezulassungen | DNV | |
| Lebensmittelzulassung | ISEGA LFGB EG 1935/2004 | |

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Note
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Ceramic BL



Surface pre-treatment

The successful application of WEICON Ceramic BL depends on the thorough preparation of the surfaces. This is the most important factor for overall success. Dust, dirt, oil, grease, rust and moisture or wetness have a negative impact on the adhesion. Therefore, before processing WEICON Ceramic BL, the following points must be observed: The surfaces must be free of any oil, grease, dirt, rust, oxides, paint and other impurities or residues. For cleaning and degreasing, we recommend WEICON Cleaner Spray S.

Smooth and particularly heavily soiled surfaces should additionally be treated by mechanical surface pre-treatment, e.g. by grinding or preferably by blasting. In case of blasting, the surface should be brought to a degree of purity of SA 2 ½ - "Near White Blast Cleaning" (according to ISO 8501/1-2, NACE, SSPC, SIS). In order to achieve an optimum surface roughness of 75 - 100 µm, angular, disposable blasting media (aluminum oxide, corundum) should be used. The surface quality is negatively influenced by the use of reusable blasting media (slag, glass, quartz), but also by ice blasting. The air for blasting must be dry and oil-free. Metal parts that have come into contact with sea water or other salt solutions should first be rinsed thoroughly with demineralised water and, if possible, left to rest overnight so that all salts can be dissolved from the metal. Before each application of WEICON Ceramic BL, a test for soluble salts should be carried out according to the Bresle method (DIN EN ISO 8502-6). The maximum amount of soluble salts remaining on the substrate should not exceed 40 mg/m². Heating and repeated blasting of the surface may be necessary to remove all soluble salts and moisture. After each mechanical pre-treatment, the surface should be cleaned again with WEICON Cleaner Spray S and protected from further contamination until the coating is applied. Areas where no adhesion to the substrate is desired must be treated with silicone-free mould release agents. For smooth surfaces, we recommend WEICON Mould Release Agent Liquid F 1000 or, for porous surfaces, WEICON Mould Release Agent Wax P 500. After the surface pre-treatment, WEICON Ceramic

BL should be applied as soon as possible (within one hour) to avoid oxidation, flash rust or new contamination.

Mixing

First, stir the resin. Then mix the resin and hardener together thoroughly and bubble-free for at least four minutes at 20°C (68°F). The included processing spatula or a mechanical mixer, such as the Stirrer Stainless Steel, can be used for this purpose. With mechanical mixers, a low speed of max. 500 rpm should be used. The components should be stirred until a homogeneous mixture is achieved. The mixing ratio of the two components must be strictly observed, as otherwise, strongly deviating physical values will result (max. deviation + /- 2 %). Only prepare a batch as large as can be processed within the pot life of 55 minutes. The indicated pot life time refers to a material batch of 500g and 20°C (68° F) material temperature. Mixing larger quantities or higher processing temperatures will result in faster curing due to the typical reaction heat of epoxy resins.



Application

For processing, we recommend an ambient temperature of 20°C (68°C) at less than 85% relative humidity. The highest adhesive strength is achieved when the parts to be processed are heated to >35°C (>95°F) before application. For a thin pre-coat, work WEICON Ceramic BL intensively into the surface in crosswise layers using a paint brush to achieve maximum adhesion. By means of this technique, the epoxy resin penetrates well into all cracks and roughness depths. Afterwards, a second application with a paint brush or foam roller can be carried out straight away, until the desired layer thickness is reached. A layer of approx. 0.25 to 0.50 mm can be achieved per work step. Make sure that the epoxy resin is applied evenly and without air bubbles. Further coats can be applied in each case after approx. 5 hours (layer sequence time).

Curing

Final hardness is reached after 24 hours at 20°C (68°F) at the latest. At lower temperatures, the curing can be accelerated by evenly applying heat up to max. 40°C (104°F), e.g. with a heating pack, hot air blower or fan heater. Higher temperatures shorten the curing time. The following rule of thumb applies: Each increase by +10°C (50°F) above room temperature (20°C/68°F) will decrease the curing time by half. Temperatures below 16°C (61°F) increase the curing time,

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es

WEICON Italia S.r.l. Italy phone +39 (0) 010 2924 871 info@weicon.it

DANLUBE A/S
Tune Parkvej 5
DK-4030 Tune
Danmark

+45 70 25 12 80
info@danlube.dk
www.danlube.dk

WEICON Ceramic BL

until at approx. 5°C (41°F) and below, almost no reaction will take place at all.

Storage

Store WEICON Ceramic BL at room temperature in a dry place. Unopened containers can be stored at temperatures of +18°C to +28°C for at least 36 months after delivery date. Opened containers must be used up within 6 months.

Scope of delivery

Processing Spatula | Instructions for Use | Gloves

Accessories

- 11202500 Cleaner Spray S, 500 ml, transparent
- 15200005 Cleaner S, 5 L, colourless, transparent
- 11207400 Surface Cleaner, 400 ml, transparent
- 15207005 Surface Cleaner, 5 L, transparent
- 10604025 Mould Release Agent Liquid F 1000, 250 ml, white, milky
- 10604515 Mould Release Agent Wax P 500, 150 g
- 10539115 Repair Stick Multi-Purpose, 115 g, vintage white
- 10700005 WEICON GL, 0,5 kg, green
- 10700010 WEICON GL, 1 kg, green
- 10850005 Glass Fibre Cloth Tape, 1 PCE, dark grey
- 10953001 Processing spatula, 1 PCE
- 10953003 Processing spatula, 1 PCE
- 10953021 Flat brush, natural bristles, 1 PCE
- 10953010 Stirrer Stainless Steel, 1 PCE
- 15841500 Pump Dispenser WPS 1500, 1,5 L
- 13955001 Empty cartridge, 1 PCE
- 52000035 Cable Scissors No. 35, 1 PCE
- 10851010 Processing Kit, 1 PCE

Recommended equipment

- Angle grinder
- Blast machine
- Heating pack
- hot air blower or fan heater
- Smoothing trowel, spatula
- PE foil 0.2 mm
- Fabric tape
- Paint brush, foam roller
- Lint-free cloths

Conversion table

| | |
|----------------------|----------------------|
| (°C x 1,8) + 32 = °F | Nm x 8,851 = lb-in |
| mm/25,4 = inch | Nm x 0,738 = lb-ft |
| µm/25,4 = mil | Nm x 141,62 = oz-in |
| N x 0,225 = lb | mPa·s = cP |
| N/mm² x 145 = psi | N/cm x 0,571 = lb/in |
| MPa x 145 = psi | kV/mm x 25,4 = V/mil |

Available sizes:

- 10400002 WEICON Ceramic BL, 200 g, blue
- 10400005 WEICON Ceramic BL, 0,5 kg, blue
- 10400020 WEICON Ceramic BL, 2 kg, blue

| | WEICON A | WEICON B | WEICON BR | WEICON C | WEICON F | WEICON F2 | WEICON HB 300 | WEICON SF | WEICON ST | WEICON TI | WEICON UW | WEICON WR2 | WEICON HP | WEICON Ceramic BL | WEICON GL | WEICON GL-S | WEICON Ceramic W | WEICON Ceramic HC 220 | WEICON WP | WEICON WR | WEICON CBC | |
|-------------------------|----------|----------|-----------|----------|----------|-----------|---------------|-----------|-----------|-----------|-----------|------------|-----------|-------------------|-----------|-------------|------------------|-----------------------|-----------|-----------|------------|---|
| Repair and moulding | x | x | x | x | x | x | x | x | x | x | x | x | | | | | | | | | | |
| Adhesive | | | | x | x | | x | | x | | | | x | | | | | | | | | |
| Wear protection | | | | | | | | | | | | | | x | x | x | x | x | x | | | |
| Potting and gap filling | x | | | | | x | | | | | | x | | | | | | | | | x | x |

To the product detail page:



Note
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C., United Arab Emirates phone +971 4 880 25
05 info@weicon.ae

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533
013 info@weicon.cz

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322
0 info@weicon.de

WEICON Inc. Canada phone +1 877 620
8889 info@weicon.ca

WEICON Ibérica S.L. Spain phone +34 (0)
914 7997 34 info@weicon.es

WEICON Italia S.r.l. Italy phone +39 (0)
010 2924 871 info@weicon.it

DANLUBE A/S
Tune Parkvej 5
DK-4030 Tune
Danmark

+45 70 25 12 80
info@danlube.dk
www.danlube.dk

WEICON Ceramic BL

Chemical resistance of WEICON Plastic Metals after curing* (Excerpt)

| | | | |
|---|---|--|---|
| Exhaust fumes | + | Potassium carbonate | + |
| Acetone | o | Potassium hydroxide 0-20 % (caustic potash) | + |
| Ethyl ether | + | Milk of lime | + |
| Ethyl alcohol | o | Carbolic acid | - |
| Ethylbenzene | - | Creosote oil | - |
| Alkalis (alkaline substances) | + | Cresylic acid | - |
| Hydrocarbons, aliphatic (petroleum derivatives) | + | Magnesium hydroxide | + |
| Formic acid >10 % (methanoic acid) | - | Maleic acid (cis-ethylenedicarboxylic acid) | + |
| Ammonia anhydrous 25% | + | Methanol (methyl alcohol) <85 % | - |
| Amyl acetate | + | Mineral oil | + |
| Amyl alcohol | + | Naphthalene | - |
| Hydrocarbons, aromatic (benzene, toluene, xylene) | + | Naphthene | - |
| Barium hydroxide | + | Sodium carbonate (soda) | + |
| Petrol (92-100 octane) | + | Sodium bicarbonate (sodium hydrogen carbonate) | + |
| Hydrobromic acid <10 % | + | Sodium chloride (table salt) | + |
| Butyl acetate | + | Sodium hydroxide >20 % (caustic soda) | o |
| Butyl alcohol | + | Caustic soda | + |
| Calcium hydroxide (slaked lime) | + | Heating oil, diesel | + |
| Chloroacetic acid | - | Oxalic acid <25 % (ethanedioic acid) | + |
| Chloroform (trichlormethane) | o | Perchloraethylene | o |
| Chlorosulphuric acid (wet and dry) | - | Kerosene | + |
| Chlorinated water (swimming pool concentration) | + | Oils, vegetable and animal | + |
| Hydrochloric acid | + | Phosphoric acid <5% | + |
| Chromium bath | + | Phthalic acid, phthalic anhydride | + |
| Chromic acid | + | Crude oil | + |
| Diesel fuels | + | Nitric acid <5% | o |
| Mineral oil and mineral oil products | + | Hydrochloric acid <10 % | + |
| Acetic acid diluted <5% | + | Sulphur dioxide (wet and dry) | + |
| Ethanol <85 % (ethyl alcohol) | + | Carbon disulphide | + |
| Greases, oils and waxes | + | Sulphuric acid <5% | o |
| Hydrofluoric acid diluted | o | White spirit | + |
| Tannic acid diluted <7% | + | Carbon tetrachloride (tetrachloromethane) | + |
| Glycerin (trihydroxipropane) | + | Tetralin (tetrahydronaphthalene) | o |
| Glycol | o | Toluene | - |
| Humic acid | + | Hydrogen peroxide <30 % (hydrogen superoxide) | + |
| Impregnating oils | + | Trichloraethylene | o |
| Potash | + | Xylene | - |

+ = resistant 0 = for a limited time - = not resistant *The storage of all WEICON Plastic Metal types was carried out at +20°C chemical temperature.

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25
05 info@weicon.ae

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533
013 info@weicon.cz

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322
0 info@weicon.de

WEICON Inc. Canada phone +1 877 620
8889 info@weicon.ca

WEICON Ibérica S.L. Spain phone +34 (0)
914 7997 34 info@weicon.es

WEICON Italia S.r.l. Italy phone +39 (0)
010 2924 871 info@weicon.it

DANLUBE A/S
Tune Parkvej 5
DK-4030 Tune
Danmark

+45 70 25 12 80
info@danlube.dk
www.danlube.dk