

# WEICON Epoxy Resin Putty



**high-strength | versatile | temperature-resistant up to +200 °C**

WEICON Epoxy Resin Putty is a metal-free, kneadable 2-component compound. The product can be used for various purposes. It is suitable for the reconditioning and repair of castings, the rebuilding of shafts, slide bearings, pumps and housings, the renewal of defective threads, the production of templates and models, and for repair works on aluminium, light metal and injection moulded parts. The compound can be used to seal pipes and tanks and to fix screws and hooks. It can be used to remove corrosion damage and pitting or to repair holes and blowholes. Epoxy Resin Putty adheres particularly well to all metals and also to ceramics, glass, stone, concrete, wood, rubber and many plastics. When cured, WEICON Epoxy Resin Putty is machinable, paintable and resistant to petrol, oil, esters, salt water and most acids and alkalis. It has a high-temperature-resistance up to +200°C (+392°F), is non-magnetic and non-corrosive. Due to the simple mixing ratio of 1:1 by weight and volume, resin and hardener can be portioned very easily in the desired quantity. WEICON Epoxy Resin Putty can be used in machine construction, tool construction, model and mould making, and in many other industrial applications.

## Characteristics

Base	epoxy
Filler	mineral
Texture	modelling
	compound
Colour	green

## Processing

Processing temperature	+15°C to +40°C	
Component temperature	>3 °C above dew point	
relative air humidity	< 85 %	
Mixing ratio by weight	100:100	
Mixing ratio by volume	100:100	
Density of the mixture	2 g/cm <sup>3</sup>	
Consumption	Layer thickness 1.0 mm	2.0 kg/m <sup>2</sup>
max. layer thickness	per step	20 mm

## Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es

WEICON Italia S.r.l. Italy phone +39 (0) 010 2924 871 info@weicon.it

## Curing

Pot life	at 20 °C, 25 g batch	20 min.
Working strength after	(80 % strength)	2 h
Final strength	(100 % strength)	5 h
Shrinkage		0,06 %

## Mechanical properties after curing

Tensile strength	DIN EN ISO 527-2	19 MPa
Elongation at break (tensile)	DIN EN ISO 527-2	< 1,0 %
E-modulus (tensile)	DIN EN ISO 527-2	1200-1600 MPa
Compressive strength	DIN EN ISO 604	80 MPa
Bending strength	DIN EN ISO 178	56 MPa
Hardness (Shore D)	DIN ISO 7619	85±3
Adhesive strength	DIN EN ISO 4624	8 MPa

## Thermal parameters

Temperature resistance		-35°C to +200°C
Tg after curing at room temperature	(DSC)	~ +49 °C
Heat deflection resistance	DIN EN ISO 75-2	+50 °C
Thermal expansion coefficient	ISO 11359	18-10-6 1/m·K

## Electrical parameters

magnetic	no
----------	----

## Specific properties

IMPA Code	812952/53/54
ISSA Code	75.509.37/38/39

## Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Surface pre-treatment

The successful application of WEICON Epoxy Resin Putty depends on the careful preparation of the surfaces, as this is a decisive factor for the success of the application. Dust, dirt, oil, grease, rust and moisture or wetness have a negative impact on the adhesion. Therefore, before processing, the following points must be observed: The areas to be bonded or repaired must be free of any oil, grease, dirt, rust, oxides, paint and other impurities or residues. For cleaning and degreasing, we recommend WEICON Cleaner Spray S.

Smooth and particularly heavily soiled surfaces should additionally be treated by mechanical surface pre-treatment, e.g. by grinding or preferably by blasting. In case of blasting, the surface should be brought to a degree of purity of SA 2 1/2 - "Near White Blast Cleaning" (according to ISO 8501/1-2, NACE, SSPC, SIS). In order to achieve an optimum surface roughness of 75 - 100 µm, angular, disposable blasting media (aluminum oxide, corundum) should be used. The surface quality is negatively influenced by the use of reusable blasting media (slag, glass, quartz), but also by ice blasting. The air for blasting must be dry and oil-free. Metal parts that have come into contact with sea water or other salt solutions should first be rinsed thoroughly with demineralised water and, if possible, left to rest overnight so that all salts can be dissolved from the metal. Before each application of WEICON

**DANLUBE A/S**  
Tune Parkvej 5  
DK-4030 Tune  
Danmark

**+45 70 25 12 80**  
[info@danlube.dk](mailto:info@danlube.dk)  
[www.danlube.dk](http://www.danlube.dk)

# WEICON Epoxy Resin Putty

Epoxy Resin Putty, a test for soluble salts should be carried out according to the Bresle method (DIN EN ISO 8502-6).

The maximum amount of soluble salts remaining on the substrate should not exceed 40 mg/m<sup>2</sup>. Heating and repeated blasting of the surface may be necessary to remove all soluble salts and moisture.

After each mechanical pre-treatment, the surface should be cleaned again with WEICON Cleaner Spray S and protected from further contamination until the coating is applied.

Areas where no adhesion to the substrate is desired must be treated with silicone-free mould release agents. For smooth surfaces, we recommend WEICON Mould Release Agent Liquid F 1000 or, for porous surfaces, WEICON Mould Release Agent Wax P 500.

After the surface pre-treatment, WEICON Epoxy Resin Putty should be applied as soon as possible (within one hour) to avoid oxidation, flash rust or new contamination.

## Mixing

Then mix the resin and hardener together thoroughly and bubble-free by kneading and rolling for at least four minutes at 20°C (68°F). The components should be stirred until a homogeneous mixture with a uniform green colour is achieved. The mixing ratio of the two components must be strictly observed, as otherwise, strongly deviating physical values will result (max. deviation +/- 2 %). Only prepare a batch as large as can be processed within the pot life of 20 minutes. The specified pot life refers to a material batch of 100 g and 20°C (68°F) material temperature. Mixing larger quantities or higher processing temperatures will result in faster curing due to the typical reaction heat of epoxy resins. Temperatures below 10°C may cause the product to harden. Brief heating to 30°C restores the usual suppleness.

## Application

For processing, we recommend an ambient temperature of 20°C (68°F) at less than 85% relative humidity. The highest adhesive strength is achieved when the parts to be processed are heated to >35°C (>95°F) before application. For a thin pre-coat, work WEICON Epoxy Resin Putty intensively into the surface in crosswise layers using a putty knife to achieve maximum adhesion. By means of this technique, the epoxy resin penetrates well into all cracks and roughness depths. Afterwards, further applications can be carried out straight away, until the desired layer thickness is reached. Make sure that the epoxy resin is applied evenly and without air bubbles. To fill large gaps or holes, fibreglass, expanded metal or other mechanical fixing materials should be used. Finally, the surface can be smoothed easily with the help of a PE film and a rubber roller.

## Processing

Knead resin and hardener in the ratio 1:1, until the mixture has a uniform green colour. Then stick onto the clean bonding surface. In order to bridge cavities, the use of glass fibre cloth is recommended. The cured material can be machined (e.g. drilled, filed, milled) and painted without pre-treatment.

## Curing

Final hardness is reached after five hours at 20°C (68°F) at the latest. At lower temperatures, the curing can be accelerated by evenly applying heat up to max. 40°C (104°F), e.g. with a heating pack, hot air blower or fan heater. Higher temperatures shorten the curing time. The following rule of thumb applies: Each increase by +10°C (50°F) above room temperature (20°C/68°F) will decrease the curing time by half. Temperatures below 16°C (61°F) increase the curing time, until at approx. 5°C (41°F) and below, almost no reaction will take place at all.

## Storage

Store WEICON Epoxy Resin Putty at room temperature in a dry place. Unopened containers can be stored at temperatures of +18°C to +28°C for at least 36 months after delivery date. Opened containers must be used up within 6 months.

## Accessories

11202500	Cleaner Spray S, 500 ml, transparent
15200005	Cleaner S, 5 L, colourless, transparent
11207400	Surface Cleaner, 400 ml, transparent
15207005	Surface Cleaner, 5 L, transparent
10604025	Mould Release Agent Liquid F 1000, 250 ml, white, milky
10604515	Mould Release Agent Wax P 500, 150 g
10850005	Glass Fibre Cloth Tape, 1 PCE, dark grey
10953001	Processing spatula, 1 PCE
10953003	Processing spatula, 1 PCE
10953020	Contour Spatula Flexy, 1 PCE
15841500	Pump Dispenser WPS 1500, 1,5 L
52000035	Cable Scissors No. 35, 1 PCE
10851010	Processing Kit, 1 PCE

## Recommended equipment

Angle grinder Blast machine Heating pack, hot air blower or fan heater Putty Knife Spatula PE foil 0.2 mm Fabric tape Rubber roller Lint-free cloths

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

# WEICON Epoxy Resin Putty

## Conversion table

$(^{\circ}\text{C} \times 1,8) + 32 = ^{\circ}\text{F}$   
 $\text{mm}/25,4 = \text{inch}$   
 $\mu\text{m}/25,4 = \text{mil}$   
 $\text{N} \times 0,225 = \text{lb}$   
 $\text{N}/\text{mm}^2 \times 145 = \text{psi}$   
 $\text{MPa} \times 145 = \text{psi}$

$\text{Nm} \times 8,851 = \text{lb}\cdot\text{in}$   
 $\text{Nm} \times 0,738 = \text{lb}\cdot\text{ft}$   
 $\text{Nm} \times 141,62 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$   
 $\text{N}/\text{cm} \times 0,571 = \text{lb}/\text{in}$   
 $\text{kV}/\text{mm} \times 25,4 = \text{V}/\text{mil}$

## Available sizes:

10500100 WEICON Epoxy Resin Putty, 100 g, green  
10500400 WEICON Epoxy Resin Putty, 0,4 kg, green  
10500800 WEICON Epoxy Resin Putty, 0,8 kg, green

To the product detail page:



### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o. Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG (Headquarters)  
Germany phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Inc. Canada phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.l. Italy phone +39 (0) 010 2924 871  
info@weicon.it

**DANLUBE A/S**  
Tune Parkvej 5  
DK-4030 Tune  
Danmark

**+45 70 25 12 80**  
[info@danlube.dk](mailto:info@danlube.dk)  
[www.danlube.dk](http://www.danlube.dk)

# WEICON Epoxy Resin Putty

## Chemical resistance of WEICON Plastic Metals after curing\* (Excerpt)

Exhaust fumes	+	Potassium carbonate	+
Acetone	o	Potassium hydroxide 0-20 % (caustic potash)	+
Ethyl ether	+	Milk of lime	+
Ethyl alcohol	o	Carbolic acid	-
Ethylbenzene	-	Creosote oil	-
Alkalis (alkaline substances)	+	Cresylic acid	-
Hydrocarbons, aliphatic (petroleum derivatives)	+	Magnesium hydroxide	+
Formic acid >10 % (methanoic acid)	-	Maleic acid (cis-ethylenedicarboxylic acid)	+
Ammonia anhydrous 25%	+	Methanol (methyl alcohol) <85 %	-
Amyl acetate	+	Mineral oil	+
Amyl alcohol	+	Naphthalene	-
Hydrocarbons, aromatic (benzene, toluene, xylene)	+	Naphthene	-
Barium hydroxide	+	Sodium carbonate (soda)	+
Petrol (92-100 octane)	+	Sodium bicarbonate (sodium hydrogen carbonate)	+
Hydrobromic acid <10 %	+	Sodium chloride (table salt)	+
Butyl acetate	+	Sodium hydroxide >20 % (caustic soda)	o
Butyl alcohol	+	Caustic soda	+
Calcium hydroxide (slaked lime)	+	Heating oil, diesel	+
Chloroacetic acid	-	Oxalic acid <25 % (ethanedioic acid)	+
Chloroform (trichlormethane)	o	Perchloraethylene	o
Chlorosulphuric acid (wet and dry)	-	Kerosene	+
Chlorinated water (swimming pool concentration)	+	Oils, vegetable and animal	+
Hydrochloric acid	+	Phosphoric acid <5%	+
Chromium bath	+	Phthalic acid, phthalic anhydride	+
Chromic acid	+	Crude oil	+
Diesel fuels	+	Nitric acid <5%	o
Mineral oil and mineral oil products	+	Hydrochloric acid <10 %	+
Acetic acid diluted <5%	+	Sulphur dioxide (wet and dry)	+
Ethanol <85 % (ethyl alcohol)	+	Carbon disulphide	+
Greases, oils and waxes	+	Sulphuric acid <5%	o
Hydrofluoric acid diluted	o	White spirit	+
Tannic acid diluted <7%	+	Carbon tetrachloride (tetrachloromethane)	+
Glycerin (trihydroxipropane)	+	Tetralin (tetrahydronaphthalene)	o
Glycol	o	Toluene	-
Humic acid	+	Hydrogen peroxide <30 % (hydrogen superoxide)	+
Impregnating oils	+	Trichloraethylene	o
Potash	+	Xylene	-

+ = resistant 0 = for a limited time - = not resistant \*The storage of all WEICON Plastic Metal types was carried out at +20°C chemical temperature.

**Note**  
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

**DANLUBE A/S**  
Tune Parkvej 5  
DK-4030 Tune  
Denmark

**+45 70 25 12 80**  
[info@danlube.dk](mailto:info@danlube.dk)  
[www.danlube.dk](http://www.danlube.dk)

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es

WEICON Italia S.r.l. Italy phone +39 (0) 010 2924 871 info@weicon.it